

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : OSLEK FLOORING PTY LTD
5 SILVER GROVE
NUNAWADING VIC 3131

TEST NUMBER : 7-598895-JV
ISSUE DATE : 11/08/2014
PRINT DATE : 11/08/2014

SAMPLE DESCRIPTION Clients Ref: "European Oak"
Engineered European Oak Flooring
Nominal Thickness: 15mm
Colour: Oak

AS/NZS 4586:2013 Slip Resistance Classification of New Pedestrian
APPENDIX A Surface Materials
Wet Pendulum Test Method

	Specimen Number					
	1	2	3	4	5	SRV
British Pendulum Number	48	44	48	47	48	47

Classification: P4

Sampling and direction of test: Sampling conducted by client.
Preparation: Washed with water and pH neutral detergent, rinsed with water,
then dried.


Fixed/Unfixed: Unfixed
Air Temperature: 20degC
Test Equipment: Munroe Stanley Skid Resistance Tester (Pendulum)
Serial Number: 0320
Slider Rubber: Slider 96 Batch No. 54, prepared on a P400 and 3um
lapping film

These results apply only to the specimens tested and it is recommended that
before selection of flooring or paving materials the effect of service
conditions, including maintenance and wear on their slip resistance,
be checked.

Tested by ATTAR




APPROVED SIGNATORY


MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR